PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



		monal Bulcau
INTERNATIONAL APPLICATION PUBLISH	HED (JNDER THE PATENT COOPERATION TREATY (PCT)
(51) International Patent Classification 7:		(11) International Publication Number: WO 00/68282
C08F 26/06, 126/06, 26/08, 26/10, 4/12, A61K 31/79, 7/06, 7/11	A1	(43) International Publication Date: 16 November 2000 (16.11.00)
 (21) International Application Number: PCT/US (22) International Filing Date: 5 April 2000 ((30) Priority Data: 09/307,211 7 May 1999 (07.05.99) (71) Applicant: ISP INVESTMENTS INC. [US/US]; 818 ton Street, Wilmington, DE 19801 (US). (72) Inventors: JACHOWICZ, Janusz; 14 Aunt Pattr Bethel, CT 06801 (US). LIU, Kou-Chang; 11 Place, Wayne, NJ 07470 (US). MC MULLER L., Jr.; 200 Franklin Street, Bloomfield, NJ 076 WINKLER, Thomas; 45 Belle Avenue, Mays 07607 (US). (74) Agents: MAUE, Marilyn, J. et al.; International Products, 1361 Alps Road, Wayne, NJ 07470 (US) 	Washin y's Lan Drayt N, Rog 003 (U) wood, 1	BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published With international search report.
(54) Title: CONDITIONING/STYLING TERPOLYMER	:S	
(57) Abstract		
What is described herein are conditioning/styling (DMAPMA) and C ₉ -C ₂₄ alkyl dimethylamino-propyl me	thacryl	ymers of vinylpyrrolidone (VP), dimethylaminopropyl methacrylamide ic acid quaternized monomers (QDMAPMA), in a defined compositional olymers exhibit advantageous low tackiness and high humidity resistance.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia	
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia	
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal	
ΑU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland	
AZ	Azerbaijan	GB	United Kingdom	MC	Мопасо	TD	Chad	
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo	
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan	
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan	
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey	
BG	Bulgaria	IIU	Hungary	ML	Mali	TT	Trinidad and Tobago	
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine	
BR	Brazil	IL	[srae]	MR	Mauritania	UG	Uganda	
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America	
CA	Canada	ГT	Îtaly	MX	Mexico	UZ	Uzbekistan	
CF	Central African Republic	JP	Јарап	NE	Niger	VN	Viet Nam	
CG	Congo	KE	Kenya	NL	Netherlands	YÜ	Yugoslavia	
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	zw	Zimbabwe	
CI	Côte d'Ivoire	KP	Democratic People's	NZ.	New Zealand			
CM	Cameroon		Republic of Korea	PL	Poland			
C7V	China	KR	Republic of Korea	PT	Portugal		•	
CU	Cuba	KZ	Kazakstan	RO	Romania			
CZ	Czech Republic	1.C	Saint Lucia	RU	Russian Federation			
DE	Germany	LI	Liechtenstein	SD	Sudan			
DK	Denmark	LK	Sri Lanka	SE	Sweden			
EE	Estonia	LR	Liberia	SG	Singapore			
								- }
								ı

WO 00/68282 PCT/US00/09065

1

CONDITIONING/STYLING TERPOLYMERS

BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to polymers for use in hair and skin care compositions, and, more particularly, to conditioning and styling terpolymers having advantageous low tackiness and high humidity resistance.

2. Description of the Prior Art

Copolymers of VP and DMAPMA have been used extensively as active components of hair and skin compositions. While these copolymers are generally suitable polymers for such products as conditioners and shampoos, it is desired to provide new polymers having improved performance characteristics in these and other personal care products.

SUMMARY OF THE INVENTION

What is described herein is a terpolymer of vinylpyrrolidone (VP), dimethylaminopropyl methacrylamide (DMAPMA) and C_9 - C_{24} alkyl dimethylaminopropyl methacrylic acid quaternized monomers (QDMAPMA), within a defined compositional range, for use in hair and skin care compositions, which are characterized by low tackiness and high humidity resistance.

DETAILED DESCRIPTION OF THE INVENTION

The terpolymers of the invention comprises the following X, Y, and Z monomers, having the formulas given below:

where:

X is a vinyl cyclic amide, e.g. vinyl pyrrolidone; n=3 to 6; R is H or C_1-C_5 alkyl and wt% of X=40-95; preferably 60-90;

where:

Y is a derivative of acrylic acid; P is O or NR_2 ; R_1 , R_2 , R_3 , R_4 are independently H or C_1 - C_5 alkyl; R_5 is C_2 - C_{16} alkyl alkylene; and wt% of Y = 0.1 to 55; preferably 5-30;

where:

Z is a quaternized derivative of an acrylic acid; P is O or NR₂; R_1 , R_2 , R_3 , R_4 are independently H or C_1 - C_5 alkyl; R_5 is a C_2 - C_{16} alkylene; and R_6 is C_9 - C_{24} alkyl; M is a halide, tosylate or phosphate anion; and wt% of Z = 0.25 to 50, preferably 1-30.

The terpolymers of the invention are hydrophobically-modified cationic polymers having long alkyl-chains therein. A typical terpolymer thus has the following formulas:

Suitably, monomer Z is prepared by tosylating DMAPMA as follows:

$$\begin{array}{c} \text{CH}_2\text{=CH} \\ \downarrow \\ \text{C=O} \\ \downarrow \\ \text{DMAPMA} + \text{Dodecyltosylate} & \longrightarrow \\ \text{NH} \\ \downarrow \\ \text{Ts}^\oplus \\ \downarrow \\ \text{C}_{12} \end{array}$$

In preferred embodiments of the invention,

X is vinyl pyrrolidone;

Y is dimethylaminopropyl methacrylamide, and

Z is a $C_{12}\text{-}C_{18}$ alkyl quaternized derivative of an acrylic acid;

X is about 60-90 wt%, Y is about 5-30 wt% and Z is about 1-30 wt%; Z is C₁₂ alkyl quaternized monomer; the weight average molecular weight of the terpolymer is 200,000 to 2,000,000; preferably 400,000 to 800,000; it is water soluble or water dispersible; and forms a clear humidity resistant, hydrophobic film when cast upon a support surface; which is surface active and hydrolytically stable; and is a homogeneous terpolymer.

Cosmetic compositions of advantageous properties including about 0.1 to 10% by weight of the terpolymer can be prepared conveniently in this invention.

Preferably, the homogeneous terpolymers of the invention are made according to the method described by Kou-Chang Liu et al. in U.S. Patent 5,626,836.

EXAMPLE 1

The preparation of (dodecyldimethyl methacryloimidopropyl ammonium tosylate). [DMAPMA-C₁₆Ts] A mixture of 360 g of dodecyl tosylate and 200 g of DMAPMA were slowly heated up to 70°C without a solvent. Stirring was continued at 70°C for 2 hours. Then the reaction was cooled to room temperature and solidified product was further used in polymerization without purification.

EXAMPLE 2

Terpolymer of VP/DMAPMA/DMAPMAA-C12Ts Quat

N-Vinylpyrrolidone (VP) (280 g) and deionized water (1400 g) are charged into a 2-liter resin pot equipped with a gas inlet, liquid inlet, a thermometer, and a condenser. The pH of the solution is adjusted to about Then a stream of nitrogen is introduced 7.5 with KOH. which bubbles through the solution during the reaction. The solution is gradually heated to 65°C for Lupersol® 11 catalyzed reaction, or to 78°C for a Vazo® 67 initiated Then, DMAPMA (17.5 g) and DMAPMAA-C₁₂Ts quat process. (52.5 g) are added continuously and uniformly into the pot with vigorous stirring for 4 hours so that the relative concentrations of the monomeric VP, DMAPMA, and DMAPMAA-C12Ts quat monomer remain practically constant throughout the reaction at predetermined levels.

As soon as DMAPMA and the DMAPMAA-C₁₂Ts quat are introduced into the pot, Lupersol® 11 (t-butylperoxy pivalate in mineral spirits) or Vazo® 67 2,2-azobis(2-methylbutanenitrile), catalyst is added. The rate of the addition of the catalyst is such that 2 ml of Lupersol is completely delivered in 4 hours. Then the solution is held for an additional 3 hours at 68°C (or 78°C for Vazo 67 initiator). The product is an aqueous solution of a homogeneous terpolymer of VP, DMAPMA and a DMAPMAA-C₁₂Ts quat has a predetermined composition indicative of the relative amounts of each monomer used in the process and is substantially free of any residual homopolymer or copolymer. The yield of the terpolymer product is substantially quantitative.

EXAMPLES 1-6
Terpolymers of VP/DMAPMA/QDMAPMAA-DTs
(Dodecyl Tosylate Hydrophobe)

Ex.	Composition (wt%) VP/DMAPMA/ QDMAPMAA-DTs	Conc % w/w	M, x10 ³	D	η ×10 ³ [cps]	Resid VP [ppm]	Resid DMAPMA [ppm]	Resid HDMAPMA %C ₁₂ OH
1	74/19.3/6.7	10	540	4.7	117	210	<100	0.34
2	74/19.3/6.7	15	560	4.6	163	640	<100	0.58
3	74/19.3/6.7	10	550	4.6	34.6	640	<100	0.58
4*	80/71/12.9	20	-	-	41.4	-	-	-
5*	80/10.36/9.64	20	-	-	35	-	-	-
6*	77/20/3	20	-	-	26.8	-	-	-

^{*} Vazo 67 initiator used

Preparation of cocoyldimethyl

methacrylamidopropyl ammonium tosylate

EXAMPLE 7

A mixture of 284.4 g of C_{16} - C_{18} tosylate and 126.7 g of DMAPMA were slowly heated up to 70°C without a solvent. Stirring was continued at 70°C for 3 hours. Then the temperature was raised to 80°C and maintained for 6 hours while stirring. Then the reaction was cooled to room temperature and solidified product was further used in polymerization without purification.

WO 00/68282 PCT/US00/09065

7

EXAMPLE 8

Terpolymer of VP/DMAPMA/DMAPMAA

C₁₆-C₁₈Ts Quat.

The copolymerization of $VP/DMAPMA/DMAPMAA-C_{16}Ts$ Quat followed the same procedure as given in Example 2.

EXAMPLES 8-10

Polymers of VP/DMAPMA/DMAPMAA-C₁₆Ts (Hexadecyl Tosylate Hydrophobe)

Ex.	Composition (wt%)	Conc.	
	VP/DMAPMA/ DMAPMAA-C ₁₆ Ts	% w/w	
В	74/19.3/6.7	15	
9	74/20/6	20	
10	77/20/3	20	

EXAMPLE 11

<u>Preparation of Lauryl-Dimethyl</u> Methacrylamidopropyl Ammonium Chloride

A mixture of 350 g of DMAPMA and 280 g of chlorododecene (1.5:1) was stirred with 111.2 g of water (15%) and 6 drops of concentrated sulfuric acid. The reaction mixture was heated up to 95° C and N_2 was bubbled through it. The conversion was followed by GC. After 24 hours the reaction mixture was cooled off (95% conversion of vinyl chloride) and product was further used in polymerization without purification.

EXAMPLES 12-17
Terpolymer of VP/DMAPMA/QDMAPMA Lauryl Chloride

The terpolymerization of $VP/DMAPMA/DMAPMAA-C_{16}$ Cl quat followed the same procedure as described in Example 2.

Ex.	Composition (wt%) VP/DMAPMA/ QDMAPMAA-LCL	Conc % w/w	M. 10 ³	D	η x10 ³ [cps]	Resid VP [ppm]	Resid LCLA [ppm]	_
12	77/70/3	20	615	5.5	28	600	400	
13	74/70/6	20	510	5.4	35	600	800	
14	71/70/9	20	485	6.2	64	500	1300	
15	93.3/3.7/3	20	493	5.3	13	200	400	
16	86.5/7.5/6	20	550	6.8	14	400	800	
17	79.8/11.2/9	20	575	7.2	30	300	1300	

EXAMPLE 18 CONDITIONING CREAM RINSE FORMULATION

Part A

- 86.4% Deionized H₂O
- 0.5% SLES (Cerasynt LP; ISP)
- 0.1% NaEDTA (Ethylenediaminetetraacetic acid disodium salt dihydrate; Aldrich)

Part B

2.55 Cetyl Stearyl Alcohol (Lanette Wax O; Henkel Corporation)

Part C

10% Aculyn 46 (modified polyethylene glycol, enzymatically modified starch; Rohm & Haas)

Part_D

0.5% Conditioning Additive of Example 13

Instructions

Heat Part A to 60°C with moderately slow stirring. Add Part B to Part A once Part A appears well mixed and homogeneous. Continue slow stirring and allow solution to cool to an ambient temperature. Add Part C while stirring and eventually add Part D.

EXAMPLE 19

CONDITIONING SHAMPOO FORMULATION

Part A

- 15% Ammonium Lauryl Sulfate (Standapol A, Henkel Corporation)
- 15% Sodium Lauryl Sulfate (Rhodapon SB-8208/S, Rhône Poulenc)
- 8% Cocamidopropyl Betaine (Mitratine CB, Rhône Poulenc)
- 2% Lauramide DEA (Monamid 716, Mona Industries)

Part B

- 1% Conditioning Additive of Example 13
- 58.8% Deionized H2O

Part C

0.2% Diazolidinyl Urea/Iodopropynyl Butylcarbamate (Germall Plus, ISP)

Instructions

Heat Part A to 60°C with moderately slow stirring for approximately hr. or until solution becomes transparent. At the same time, heat Part B to 55°C while stirring until homogeneous solution is obtained. Add Part B to Part A while continuously stirring. Remove temperature source. Once the resulting solution has reached 45°C, add Part C. Continue to stir (slowly) until the target solution has cooled to an ambient temperature.

In the conditioners and shampoo formulations tested under actual use conditions in comparison with similar formulations with known polymers, the terpolymers of the invention have excellent wet combing, excellent dry feel and softness, and excellent wet feel.

Furthermore they are characterized by excellent styling properties in terms of stiffness, humidity resistance and dry and wet feel.

EXAMPLE 20

STYLING LOTION

A styling lotion formulation was prepared in aqueous solution using 1% by weight of the terpolymer of Example 1 and 0.1% preservative.

EXAMPLE 21

STYLING MOUSSE

A concentrate is prepared by dissolving 1 g of the terpolymer of Example 1, 0.1 g of preservative and 98.9 g of deionized water.


A styling mousse formation is prepared by mixing 70 g of the concentrate and 30 of hydrocarbon propellant in an aerosol can provided with a mousse dispenser.

While the invention has been described with particular reference to certain embodiments thereof, it will be understood that changes and modifications may be made which are within the skill of the art. Accordingly, it is intended to be bound only by the following claims, in which:

WHAT IS CLAIMED IS:


 A terpolymer comprised of the following monomers;

X, Y and Z;



where:

n is 3 to 6; R is H or C_1 - C_5 alkyl and wt% of X = 40-95;



where:

P is O or NR_2 ; R_1 , R_2 , R_3 , R_4 are independently H or C_1-C_5 alkyl; R_5 is C_2-C_{16} alkyl alkylene; and wt% of Y = 0.1 to 55; and

where:

P is O or NR_2 ; R_1 , R_2 , R_3 , R_4 are independently H or C_1 - C_5 alkyl; R_5 is a C_2 - C_{16} alkylene; R_6 is C_9 - C_{24} alkyl; M is a halide, tosylate or phosphate anion; and wt% of Z = 0.25 to S_0 .

- 2. A terpolymer according to claim 1 wherein:
- X is vinyl pyrrolidone,
- Y is dimethylaminopropyl methacrylamide, and
- Z is a C_{12} - C_{18} alkyl quaternized derivative of an acrylic acid.
- 3. A terpolymer according to claim 2 wherein X is about 60-90 wt%, Y is about 5-30 wt% and Z is about 1-30 wt%.
- 4. A terpolymer according to claim 2 wherein Z is C_{12} alkyl quaternized monomer.
- 5. A terpolymer according to claim 1 wherein the weight average molecular weight is 200,000 to 2,000,000.
- 6. A terpolymer according to claim 5 wherein said molecular weight is 400,000 to 800,000.

- 7. A terpolymer according to claim 2 which is water soluble or water dispersible.
- 8. A terpolymer according to claim 1 which forms a clear humidity resistant, hydrophobic film when cast upon a support surface.
- 9. A terpolymer according to claim 1 which is surface active and hydrolytically stable.
- 10. A terpolymer according to claim 1 which is a homogeneous terpolymer.
- 11. A cosmetic composition including about 0.1 to 10% by weight of the terpolymer of claim 1.
- 12. A cosmetic composition according to claim 11 which is a hair or skin care product.

INTERNATIONAL SEARCH REPORT

International application No. PCT/US00/09065

	SSIFICATION OF SUBJECT MATTER						
US CL	Please See Extra Sheet. : 526/258, 195, 264; 424/70.12, 78.24						
According to	According to International Patent Classification (IPC) or to both national classification and IPC						
	DS SEARCHED						
	ocumentation searched (classification system followe	d by classification symbols)					
U.S. :	526/258, 195, 264; 424/70.12, 78.24	·					
Documentat	ion searched other than minimum documentation to the	extent that such documents are included	in the fields searched				
Electronic d	lata base consulted during the international search (n	ame of data base and, where practicable	e, search terms used)				
	, Nonpatent literature	·					
C. DOC	UMENTS CONSIDERED TO BE RELEVANT						
Category*	Citation of document, with indication, where a	ppropriate, of the relevant passages	Relevant to claim No.				
х	U.S. 5,997,855 A [LIU] 07 Decembe	r 1999 abstract col 2 lines	1,5,6,10-12				
	48-51, 12-18, col.5, lines 3-6	1 1777, abstract, cor. 2, mos					
Y	col.2, lines 50-51, col.3, lines 23-51,	col.1, lines50-55	2-4,7-9				
A	U.S. 5,321,110 A (SHIH) 14 June 19	1-12					
Α	U.S. 5,603,919 A (LIU et al.) 18 Fel	1-12					
-	· · · · · · · · · · · · · · · · · · ·						
Α	U.S. 4,956,430 A (TAZI) 11 Septem	ber 1990	1-12				
X Furth	er documents are listed in the continuation of Box C	See patent family annex.					
	ecial categories of cited documents:	"T" later document published after the inte date and not in conflict with the appli	cetion but cited to understand				
	cument defining the general state of the art which is not considered be of particular relevance	the principle or theory underlying the	invention				
	tier document published on or after the international filing date	"X" document of particular relevance; the considered novel or cannot be consider when the document is taken alone					
Cite	coment which may throw doubts on priority claim(s) or which is ed to c. blish the publication date of another citation or other scall reason (as specified)	"Y" document of particular relevance; the					
O doc	cument referring to an oral disclosure, use, exhibition or other	considered to involve an inventive combined with one or more other such being obvious to a person skilled in the	documents, such combination				
P document published prior to the international filing date but later than *&* document member of the same paten the priority date claimed							
Date of the actual completion of the international search		Date of mailing of the international sea	rch report				
23 MAY 2000 27 JUL 2000,							
Name and mailing address of the ISA/US Authorized officer			0 //				
Box PCT	ner of Patents and Trademarks	TATYANA ZALUKAEVA					
	n. D.C. 20231 (o. (703) 305-3230	Telephone No. (703) 308-0661					

INTERNATIONAL SEARCH REPORT

International application No. PCT/US00/09065

C (Continua	tion). DOCUMENTS CONSIDERED TO BE RELEVANT	
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	U.S. 5,626,836 A (LIU et al) 06 May 1997	1-12
	·	
;		
	<u> </u>	

Form PCT/ISA/210 (continuation of second sheet) (July 1998)★

INTERNATIONAL SEARCH REPORT

International application No. PCT/US00/09065

A. CLASSIFICATION OF SUBJECT MATTER: IPC (7):	
CO8F 26/06, 126/06, 26/08, 26/10, 4/12; A6IK 31/79, 7/06, 7/11	
	ļ

Form PCT/ISA/210 (extra sheet) (July 1998) +